

# SolvoTex Artist Premium Heavy S

## Product Specifications



Material Details	
Material	100% Polyester
Weight	290 g/m <sup>2</sup> or 8.5 oz/yd <sup>2</sup>
Character	Heavy canvas structure
Coating	Coating for solvent and UV inks, bath coated
Washable	Restricted to 30°C / 85°F
Flammability	Meets NFPA 701, 2004 Test #2, B1 according to DIN 4102
Added Value	Highest brilliance, deeper black, outdoor durability up to 6 months, can be backlit and frontlit

	Art Reprographic	Display Systems	Flags	Indoor Banners	Outdoor Banners	POS	Theatrical	Tradeshow	Wall Covering
Applications	◆	❖		◆	◆	◆	❖	◆	◆

Printability	
Solvent	◆
Eco Solvent	□
UV	◆
Dye Transfer	
Dye Direct	

### Processing & Handling

- Print slowly.
- To avoid fingerprints, it is recommended that protective gloves be worn while handling.
- To prevent problems after processing / laminating, make sure all prints have been allowed sufficient time to thoroughly dry (dry time of 12 hours to be assured).

Key
□ Fair
❖ Good
◆ Excellent

Temperatures and thicknesses are given as approximate values. All data are standard values. The information in this specification sheet is based on findings obtained in practice. Because of the high number of factors which can have an effect during handling and application, customer tests will be required. A legally binding guarantee of specific properties is not to be inferred from our specifications. The information given here may be subject to change without notice. Neschen has not prepared MSDSs for these products which are not subject to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the Neschen directions for use, these products should not present a health and safety hazard. However, use or processing of the products in a manner not in accordance with the directions for use may affect their performance and present potential health and safety hazards. Information given on Miller Weldmaster is based off testing done by Miller Weldmaster and is given as a general starting point. The purchaser should test material to determine if it is suitable for their own specific purpose.

**Neschen Americas**  
 7091 Troy Hill Drive, Elkridge, MD 21075  
 Tel: 410-540-8900  
 Tech Service: 800-486-6502  
 Fax: 410-579-8960

